



V211

CLEAR COAT 4:1

E-84
version:083021

Technical data sheet

DEFINITION

V211 is a 2.1 VOC compliant clear coat. It has a superior gloss and outstanding buffing capabilities.

PHYSICAL CHARACTERISTICS

Colour:	water white
Solid wt. (as mixed):	32 %
VOC as mixed:	2.1 lbs/gal – 250 g/l

AUXILIARY PRODUCTS

C215	Standard Hardener
C216	Fast Hardener

APPLICATION

Apply V211 on the basecoat after the flash off time recommended by the manufacturer.

MIXING RATIO

V211			
C215	100:25	4:1	25°C / 77°F
C216			2h

APPLICATION METHOD

	1,3-1,5	2	8-10'









V211

CLEAR COAT 4:1

E-84
version:083021

Technical data sheet

DRY AND FLASH TIMES

25°C / 77°F			60°C/140°F		
					
C215	20'	12-24h	C215	30'	2h

SAFETY

Follow instructions of product label. For more information check the Material Safety Data Sheets (FISPQ). Complaint with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C / 40°F and +30°C / 90°F.

GUARANTEE

One year in the unopened original packaging.

These products are for professional use only. The Safety Data Sheet should be consulted before use and the precautionary warnings on the product packaging should be observed. Its correct use, according to its purpose and respecting its technical and security data, provided in these documents, is the sole and exclusive responsibility of the user. ROBERLO DO BRASIL LTDA declines any liability due to the incorrect use of any product.

The information included in this documentation is based on our scientific and technical knowledge on the date of its issuance. ROBERLO reserves the right to modify and/or discontinue all or part of the information at any time and without prior notice. It is the user's responsibility to verify the update of the information. The latest version of this document replaces all previous versions.

*All clauses contained herein apply to any future changes or modifications.
For any additional technical information please consult with our Customer Service or our Technical Department.*